

Ficha técnica L-Medium

versão - 1.24

Identificação: Pavimento em Betão Afagado L-Medium.

Descrição: Pavimento indicado para tráfego pedonal e ou viário ligeiro onde sejam consideradas reduzidas as cargas aplicadas no pavimento < 3000 kg/m².

Campos de Aplicação:

- Acessos pedonais em moradias.
- Acessos pedonais em zonas urbanísticas.
- Pequenos depósitos de materiais.
- Zonas de circulação viária.
- Serventias de habitações.

Composição técnica do pavimento:

- Malhasol CQ 38.
- Betão C25/30 XC2(P) C10,4 D12,5 S3, Pav. 12cm.
- Fibras de polipropileno à razão de 500g/m³.
- Endurecedor de superfície do tipo "Sibquartzo" à razão de 4 kg/m².
- Folha de espuma em polietileno expandido com 50mm de espessura.
- Produto de cura e de selagem.

Cores:

Este tipo de pavimento pode ser colorido consoante as necessidades e meio envolvente, as cores disponíveis podem ser consultadas em www.lusochapas.pt.

Notas: Esta ficha técnica não possui um carácter absoluto, mas sim resultado de dados adquiridos através de resultados técnicos fornecidos pelos nossos fornecedores, bem como de anos de experiência na construção de pavimentos.

L-Medium Technical Sheet

version - 1.24

Identification: Smoothed Concrete Pavement L-Medium.

Description: Pavement suitable for pedestrian and/or light road traffic where the loads applied to the pavement are considered to be reduced < 3000 kg/m².

Fields of Application:

- Pedestrian access in homes.
- Pedestrian access in urban areas.
- Small material storage areas.
- Road circulation areas.
- Household services.

Technical composition of the pavement:

- Malhasol CQ 38.
- Concrete C25/30 XC2(P) C10,4 D12,5 S3, 12cm pavement.
- Polypropylene fibers at a rate of 500g/m³.
- Sibquartzo type surface hardener at a rate of 4 kg/m².
- 50mm thick expanded polyethylene foam sheet.
- Curing and sealing product.

Colors:

This type of flooring can be coloured according to the needs and the surrounding environment. The available colors can be found at www.lusochapas.pt.

Notes: This technical sheet is not absolute, but rather the result of data acquired through technical results provided by our suppliers, as well as years of experience in flooring construction.